

Таблица 4.3.1. Термодинамические свойства жидкого лития на линии насыщения

T	p_s	ρ'	h'	s'	c_p'
453.69	2.410E-14	514.7	1702.781	6.766	4.376
500	1.079E-12	511.0	1904.394	7.189	4.332
600	5.195E-10	502.4	2333.897	7.972	4.262
700	4.165E-8	493.3	2757.544	8.625	4.214
800	1.096E-6	483.8	3177.149	9.186	4.181
900	1.378E-5	473.9	3594.054	9.677	4.159
1000	1.036E-4	463.9	4009.369	10.114	4.149
1100	5.374E-4	453.8	4424.074	10.509	4.147
1200	2.111E-3	443.7	4839.075	10.871	4.154
1300	6.710E-3	433.6	5255.234	11.204	4.170
1400	1.807E-2	423.7	5673.382	11.514	4.194
1500	4.264E-2	413.9	6094.329	11.804	4.226
1600	9.048E-2	404.3	6518.873	12.078	4.266
1700	1.759E-1	394.9	6947.803	12.338	4.314
1800	3.183E-1	385.7	7381.900	12.586	4.369
1900	5.420E-1	376.7	7821.941	12.824	4.433
2000	8.770E-1	367.9	8268.697	13.053	4.504