

Таблица 4.3.5. Термодинамические свойства жидкого калия на линии насыщения

$T$	$p_s$	$\rho'$	$h'$	$s'$	$c_p'$
336.86	1.50E-10	829.3	271.035	1.926	0.822
400	1.972E-8	814.3	322.452	2.066	0.807
500	3.349E-6	790.6	402.074	2.244	0.786
600	9.872E-5	767.3	479.897	2.386	0.771
700	1.080E-3	744.1	556.577	2.504	0.763
800	6.407E-3	720.9	632.844	2.606	0.763
900	2.536E-2	697.4	709.467	2.696	0.771
1000	7.583E-2	673.6	787.230	2.778	0.786
1100	1.852E-1	649.1	866.929	2.854	0.809
1200	3.889E-1	624.1	949.363	2.926	0.841
1300	7.270E-1	598.5	1035.337	2.995	0.880
1400	1.240	572.4	1125.655	3.061	0.928
1500.	1.965	545.6	1221.127	3.127	0.983
1600	2.930	518.0	1322.559	3.193	1.047
1700	4.155	489.2	1430.762	3.258	1.119
1800	5.647	458.3	1546.544	3.324	1.198
1900	7.405	423.8	1670.716	3.392	1.286
2000	9.418	383.4	1804.088	3.460	1.382